

Bona DriFast® Sealer

Technical data sheet

A quick drying, polyurethane sanding sealer. Designed to penetrate and seal bare wood. Compatible with all Bona® stains, oil-modified and waterborne finishes.

- Easy application
- Penetrates and seals the wood
- Fast drying – 1 ½ - 2 hours
- Rapid hardness development
- Sands easily for use as a sanding sealer
- Meets ASTM D 1640 for quick-dry sealers
- VOC Compliant under U.S. EPA regulations
- Clean up with mineral spirits

Technical data

Physical Characteristics:

Ingredients – Mineral spirits (solvent), urethane resins, silica, driers.

Color – wet – amber; dry – light amber

Solids – 37%

Density – 7.21 lbs/gallon (0.866 S.G.)

US Regulatory VOC – 550 g/L

Odor – Mineral spirits

Stability – Two-year shelf life in unopened container

Flash Point – 115° F (46° C)

Packaging – 1-gallon can, 5-gallon pail

Application Characteristics:

Clarity – Clear

Leveling – Excellent

Defoaming – Excellent/complete

Drying Time – 1-1/2 - 2 hours

Application Tools – 3/16" nap mohair roller, paint tray, natural bristle brush, T-bar, flocked foam paint pad

Coverage – 600-700 square feet per gallon

Percent Cured After 24 Hours – 60%

Maximum Cure – 2 weeks

Recommended Use

Formulated for use under all Bona® oil-modified and waterborne finishes.

Directions

BEFORE USING, READ ALL DIRECTIONS AND SAFETY DATA SHEETS

FOR TECHNICAL ADVICE: Call Bona US at 800/872-5515

COMPATIBILITY STATEMENT: Bona DRIFAST® Sealer will adhere to most stains after proper preparation and dry times. Stain, sealer and finish results may vary depending on the wood species, especially on oily and resinous exotics. ALWAYS PREPARE A SAMPLE OR TEST AREA TO DETERMINE COMPATIBILITY IF USING ANYTHING OTHER THAN A BONA® PRODUCT.

PREPARATION: SANDING AND FINISHING

1. Sand and prepare floor using accepted industry association methods. 2. Make your final cut with either a screen or MultiDisc using 80 to 120-grit abrasives. 3. Use a Tampico Brush on a buffer and vacuum thoroughly. 4. Tack with dry Bona® Microfiber Mop or cloth to remove dust. 5. Apply Bona Sealer system.

MIXING INSTRUCTIONS: STIR WELL BEFORE USING! DO NOT THIN.

SEALING:

1. Pour sealer into paint tray. Wet the 3/16" mohair roller. 2. Apply sealer to a 3'x3' section of the floor against the grain at a coverage rate of 600 – 700 square feet per gallon. 3. Without adding more sealer to roller, re-roll entire 3'x3' section with the grain of the wood. 4. Continue process throughout entire floor. Note: Apply evenly, excessive amounts of sealer may cause floor failure. 5. Allow sealer to dry thoroughly for a minimum of 2 hours under ideal conditions of 60-80° F (16° C-27° C)/ 35-75% relative humidity. High humidity and/or low temperature conditions will extend dry time while increased ventilation and airflow will reduce dry time. 6. Abrade Bona DriFast Sealer using 120-grit or finer, screen or 1-2 (stacked) Bona Conditioning Pads and 1-2 Bona Diamond 180 to 240-grit

Sealing



Bona DriFast® Sealer

Technical data sheet

abrasives. **7.** Thoroughly vacuum and dry tack with Bona Microfiber Tacking pads (or slightly dampened with water). **8.** Apply a Bona® finish according to label directions.

Maintenance

CLEAN-UP: Clean applicator tools and equipment with mineral spirits.

STORAGE AND DISPOSAL: Store in a well-ventilated place. Keep cool. Keep container closed when not in use. Do not store above 100° F (38° C). Do not transfer contents to other containers for storage and disposal. In case of spillage, absorb with inert material. Dispose of contaminated absorbent, container and unused contents in accordance with local, state and federal regulations.

DANGER: RAGS, STEEL WOOL OR WASTE SOAKED WITH DRIFAST® SEALER MAY SPONTANEOUSLY CATCH FIRE IF IMPROPERLY DISCARDED. IMMEDIATELY AFTER EACH USE, PLACE RAGS, STEEL WOOL OR WASTE IN A SEALED, WATER-FILLED METAL CONTAINER.

Order Information

Item #:	No/Case
Quart: SB750051001	6
1 Gallon: SB750018172	4
5 Gallon: SB750018173	1

Sealing



Bona®